

Kura

KEILHAUER



K1724 - White Sand



K1723 - Old Platinum



K1720 - Bisque



K1731 - Crocus



K1727 - Deep Violet




K1730 - Blue Black



K1725 - Silver Green




K1726 - Venetian



K1722 - Seal Grey



K1728 - Etruscan Red



K1729 - Chinaberry







K1721 - Forest Floor

Specifications

Kura Grade H

Content	39% Cotton, 28% Alpaca, 11% Polyester, 9% Virgin Wool, 7% Polyamide, 6% Viscose
Finish	None
Repeat	None
Weight/Linear Yard	17 oz
Width	54"

Performance characteristics

Abrasion Resistance (ASTM D4157-13) Wyzenbeek Method	100,000 double rubs Heavy duty	
Colorfastness to Light (AATCC - 16.3-2014)	40 hrs., Class 4 - 5	
Colorfastness to Crocking (AATCC - 8-2013)	dry - Class 3 - 4 wet - Class 3	
Breaking Strength (ASTM D - 5034-09-2013)	Warp: 55.3 lbs. min. Fill: 119.4 lbs. min.	
Seam Slippage (ASTM D43034-92)	Warp: 91.2 lbs. min. Fill: 21.1 lbs. min.	
Brush Pill (ASTM D4970M-16)	Class 5	

Flammability

CAL TB 117	Passes	
------------	--------	---

Recommended cleaning instructions

P	Spot staining with spray detergent dry cleaning.
---	--

Dye lots may vary slightly from samples shown.

Kura is a piece-dyed product, colors will vary from batch to batch. Keilhauer cannot guarantee an exact color match. Textile memos should be used as a reference only, with the expectation of change. For dye-lot samples, please contact Customer Service.



Visit Material Bank
to Order Samples